

WELDANO TURGA

Welding liquid in the SOLITEX WELDANO roof lining system



Technical data

Substance	
Material	Tetrahydrofuran (90 %), Cyclohexanone (10 %)
Attribute	Regulation Value
Colour	transparent
Application temperature	> 0 °C, optimally 18-20 °C ; 32 °F, optimally 64-68 °F
Storage	15 °C to 25 °C ; 60 °F to 77 °F, dry and well ventilated, only in the original container, keep away from heat and sources of ignition

Area of application

Welding liquid agent for waterproof adhesion of overlaps for roof lining membranes made of PU (e.g. SOLITEX WELDANO). Also suitable for adhesion of accessories - such as SOLITEX WELDANO-S sealing strips - that are used to seal details.

Advantages

- ✓ Economical to apply
- ✓ Reliable homogeneous bonds can quickly be subjected to loading
- ✓ Customised welding liquid in the SOLITEX WELDANO roof lining system

Substrates

Before WELDANO TURGA is applied, SOLITEX WELDANO should be wiped clean with a cloth. There must be no water-repellent substances (e.g. grease or silicone) on the subsurface.

General conditions

Shake the container or stir the contents before use. Around 200 - 250 metres (219-270 yd) of membrane length can be welded (weld joint width 30 mm; 1.2") using a litre of WELDANO TURGA. The working temperature must not be below 0 °C / 32 °F.

Use the 500 ml bottle with a brush for particularly quick and easy application.

Advantages: quick and easy application of the WELDANO TURGA solvent welding agent, allows the technician to work with one hand, no contamination of the solvent welding agent in the container, volume of 500 ml (16.9 US oz).



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

MOLL
bauökologische Produkte GmbH
Rheintalstraße 35 - 43
D-68723 Schwetzingen
Fon: +49 (0) 62 02 - 27 82.0
eMail: info@proclima.de

